

Summary of specification data - ALPOLIC®/fr SCM Stainless Steel Composite Material

1. General

ALPOLIC®/fr SCM is a stainless steel composite material with a non-combustible mineral-filled core, used as an exterior cladding and roof covering on new buildings and retrofit applications. The material is manufactured by Mitsubishi Plastics, Inc., and furnished by approved dealers or distributors.

Note: Specification data may be changed in part without affection of material quality.

2. Product composition

ALPOLIC/fr SCM is composed of a non-combustible mineral-filled core sandwiched between two skins of 0.3mm thick stainless steel:

Composition

- Topside skin material; 0.3mm thick stainless steel, NSSC 220M, a highly rust-resistant ferric stainless steel
- Core material; Non-combustible mineral filled core
- Backside skin material; 0.3mm thick stainless steel sheet, NSSC220M, a highly rust-resistant ferric stainless steel

The core has the same contents as the established fire-retardant core of ALPOLIC/fr. The topside surface is protected with a self-adhesive peel-off protective film consisting of two polyethylene layers of white and black. According to weathering tests under normal outdoor conditions, the protective film will withstand six months' exposure without losing its original peel-off characteristic or causing stains or other damages.

3. Surface finish

Hairline Finish and Dull finish ^{Note}

Note: For other finishes, contact local distributors or our office.

4. Product dimension and tolerance

- (1) Panel thickness: 4 mm
- (2) Panel size: Width = 1000 mm ^{Note}
Length = less than 5000 mm

Note: 1219mm wide product is available upon request. Contact local distributors or our office.

(3) Product tolerance

- Width: ±2.0 mm
- Length: ±4.0 mm
- Thickness: ±0.2 mm

Bow: Maximum 0.5% (5mm/m) of the length or width
 Square-ness (diagonal difference): Maximum 5.0 mm

5. Principal properties

- (1) Panel weight: 10.2 kg/m²
- (2) Thermal expansion: 10.4×10⁻⁶/°C
- (3) Deflection temperature (ASTM D648): 117°C
- (4) Sound transmission loss (ASTM E413): 30 STC (Sound Transmission Class)
- (5) Mechanical properties of SCM
- a. Tensile strength (ASTM E8): 84 MPa or N/mm²
 - b. 0.2% proof stress (ASTM E8): 69 MPa or N/mm²
 - c. Elongation (ASTM E8): 12.6 %
 - d. Flexural elasticity, E (ASTM C393): 70.6 GPa or kN/mm²
 - e. Flexural rigidity, E×I, (ASTM C393): 372 kNmm²/mm
- (6) Mechanical properties of skin metals:
- NSSC220M
 - a. 0.2% proof stress (ASTM E8): 295 MPa or N/mm²
 - b. Flexural elasticity (ASTM E8): 201 GPa or kN/mm²

6. Fire performance

In Japan, SCM is approved as a non-combustible material for exterior and interior uses, based on the fire test results of the heat release test (ISO 5660-1) and the gas toxicity test. The tests done in accordance with the UK and USA standards are only general tests for building materials, but SCM is virtually approved as an eligible material for external claddings and roof coverings in most countries on the basis of the extensive fire test results on ALPOLIC/fr. SCM 4mm has passed the following fire tests.

Country	Test standard	Result & Classification
U.K.	BS476 Part 6	Class 0
	BS476 Part 7	Class 1
U.S.A.	Tunnel test (ASTM E-84)	Class A/Class 1
Japan	Heat release test (ISO 5660-1) & gas toxicity test	Non-combustible material. Certificate No. NM-0229

7. General notes

(1) Processing method

The machinability of stainless steel is low. Therefore, we need special machines and tools for cutting and grooving SCM panels. Use a square shear or a CNC router for cutting, and use a CNC router or a V-cut machine (planer) for grooving. Refer to the fabrication manual for details.

(2) Prevention of galvanic corrosion

Stainless steel belongs to the noble metal in corrosion potential. If dissimilar metals are used for assembling SCM panels, the corrosion of the less noble metal may be accelerated with galvanic corrosion under moist circumstances. Use stainless steel rivet and stainless steel bolt/nut for joining. Use stainless steel angle and flange for accessory, if possible. When aluminum extrusions are used for accessory, insulate the aluminum surface electrically with anodizing or coating.

(3) Color variation among production lots

It is possible that the color of SCM slightly varies among production lots and the inconsistent color is visible after installation. This is caused by the slight color difference between stainless steel coils. In order to prevent this problem, we recommend placing the total requirement in one order or allotting the panels with adequate grouping arrangement.

For further information, please contact:

mitsubishi plastics, inc.
Industrial Materials Division
Composite Materials Department
2-2, Nihonbashi Hongokucho 1-chome
Chuo-ku, Tokyo 103-0021 Japan
Telephone: 81-3-3279-3064 / 3065
Facsimile: 81-3-3279-6672
E-mail: mks-ho-alpolic@cc.m-kagaku.co.jp

MITSUBISHI CHEMICAL FP AMERICA, INC.
Composite Materials Division
401 Volvo Parkway, Chesapeake, VA 23320
Telephone (USA): 800-422-7270
Telephone (International): 1-757-382-5750
Facsimile: 1-757-436-1896
E-mail: info@alpolic.com

MITSUBISHI CHEMICAL SINGAPORE PTE LTD
Composite Materials Department
79 Anson Road, #12-01 Singapore 079906
Telephone: 65-6226-1597
Facsimile: 65-6221-3373
E-mail: SIN0027@cc.m-kagaku.co.jp

Distributed by:

MITSUBISHI PLASTICS, INC.
Turkey Liaison Office
Baglarbasi Kisikli Cad., No:4, Sarkuysan-Ak Is Merkezi,
S-Blok, Teras Kat, Altunizade, Uskudar, 34664 Istanbul, Turkey
Telephone: 90-216-651-8670/71/72
Facsimile: 90-216-651-8673
E-mail: info@alpolic.com.tr

The material properties or data in this leaflet are portrayed as general information only and are not product specifications. Due to product changes, improvements and other factors, Mitsubishi Plastics, Inc. reserves the right to change or withdraw information contained herein without prior notice.

©2008 Mitsubishi Plastics, Inc. All rights reserved.

ALPOLIC® is the registered trademark of Mitsubishi Plastics, Inc.