



Promat



Cafco SPRAYFILM[®] WB3

Water Based Intumescent Coating



032-073

Cafco SPRAYFILM® WB3

Water Based Intumescent Coating

INTRODUCTION

Cafco SPRAYFILM® WB3 is a water based intumescent coating consisting of polyvinyl acetate resins and fillers for the fire protection of structural steel. It can be sealed and protected with a decorative top coat.

Cafco SPRAYFILM® WB3 is applied directly to the contour of primed I and H section columns, angles, channels and beams and hollow sections, to provide fire protection for up to 120 minutes. In a fire, a chemical reaction takes place causing the Cafco SPRAYFILM® WB3 to expand and form an insulating layer which slows the temperature of the steel rising to a critical level.



Properties and performance	
Colour and finish	White with a flat matt finish. Preferably spray applied with airless paint equipment for speed and quality of finish. Brush and roller application is also possible.
Maximum thickness per coat	Wet film thickness (WFT) at 1.6mm using spray and 0.76mm using brush. For airless spraying, several thin coats as opposed to one heavy coat will give greater control over finish and thickness.
Practical coverage	Dependent on surface texture, substrate, application method and technique.
Theoretical coverage	Approximately 18.79m ² per container (1mm per litre) at 1mm WFT = 0.7mm DFT (Dry film thickness) = 1 litre per m ² 1mm = 1000µm (microns)
Number of coats	One or more as required
Cure	By air drying
Initial set	Approximately 6 hours at 20°C and 50% RH for 0.4mm WFT
Solids by weight	70% ± 2%
Density	1.33kg/litre
Surface burning	Flame spread 5, smoke development 35 when tested to ASTM E84.
Durometer hardness	80 shore D when tested to ASTM D2240
Impact resistance	18kg/m when tested to ASTM D2794
Abrasion resistance	0.6505g/1000 cycles when tested to ASTM D4060
pH value	8.0 ± 0.2 at 25°C
Fire resistance	Structures protected with Cafco SPRAYFILM® WB3 have undergone fire resistance tests at approved independent laboratories to recognised standards throughout the world, including: <ul style="list-style-type: none"> • UK (BS476: Part 21: 1987) • Canada and USA (ASTM E119 and ASTM E84) • Australia (AS1530: Part 4) Assessed in accordance with ASFP "Fire protection for structural steel in buildings" procedures.

QUALITY ASSURANCE

Promat manufactures to a quality system in accordance with ISO 9001: 2008 and has received full accreditation to these standards.

Operating to these standards means that all activities, which have a bearing upon quality, are set out in written procedures. Systematic and thorough checks are made on all materials and their usage. Test equipment is subjected to regular checks and is referred back to national standards.

The information given in this data sheet is based on actual tests and is believed to be typical of the product. No guarantee of results is implied however, since conditions of use are beyond our control.

ADVANTAGES

- Provides fire resistance for up to 120 minutes in accordance with BS476: Part 21 and AS1530: Part 4 and up to 180 minutes in accordance with ASTM E119.
- Durable and decorative finish.
- Steelwork may be left exposed to view.
- Chemical and abuse resistant.
- Can be top coated to match surroundings.
- Easy application and clean up with water.
- Fast drying time.



Cafco SPRAYFILM® WB3

Water Based Intumescent Coating

Please consult your nearest Promat office for specific details pertaining to local conditions.

Preparation	
Typical substrates	Primed steel
Substrate preparation	<p>The substrate shall be clean, dry and free from dust, oil and any other condition preventing good adhesion.</p> <p>Before applying Cafco SPRAYFILM® WB3 to structural steel, the steel must be blast cleaned to SA 2.5 (ISO 8501-1: 1998), primed with a compatible primer approved by Promat Sprays Division and applied in full compliance with the manufacturer's recommendations.</p> <p>Primers compatible with Cafco SPRAYFILM® WB3 are generally of the following types:</p> <ul style="list-style-type: none"> ● Alkyd zinc phosphate ● Epoxy polyamide zinc phosphate ● Zinc silicate (inorganic zinc)* ● Epoxy zinc rich (organic zinc)* <p>* Tie coat required</p> <p>If left exposed for long periods zinc rich epoxies may form a layer of zinc salts on the surface. These salts must be completely removed before applying Cafco SPRAYFILM® WB3.</p>

Application	
Methods	<p>Cafco SPRAYFILM® WB3 is supplied ready for use and should not be diluted. The primer thickness should be measured and recorded prior to the application of Cafco SPRAYFILM® WB3, in order to be able to accurately check the thickness of Cafco SPRAYFILM® WB3 during and after application.</p> <p>Stir Cafco SPRAYFILM® WB3 thoroughly with a drill type mixer prior to application by either airless spray, brush or roller.</p> <p>Protect from rain and high humidity during application and drying.</p>
Thickness checking during	<p>To ensure the correct thickness is being applied, frequent measurements should be taken using a wet film thickness gauge. To determine approximate dry film thickness (DFT) based on wet film thickness (WFT), multiply WFT by 0.72.</p> <p>For example: 1.3mm WFT x 0.72 = 0.936mm DFT</p>
Limitations	<p>Take a dry film thickness reading as soon as the coating is fully cured. An Elecometer 211 permanent magnetic (magnetic banana gauge) or Elecometer 456 electromagnetic (electronic gauge) type may be used. Ensure primer thickness is deducted from final thickness reading.</p> <p>If Cafco SPRAYFILM® WB3 is left exposed, it must be protected from rain and high humidity or sealed with a topcoat appropriate for the environmental conditions. Please contact Promat for appropriate products.</p>

FIRE PROTECTION THICKNESS

The thickness of the fire protection for a given period of fire resistance in a cellulosic type fire, relates to the Hp/A ratio of the steel section. Hp/A is the ratio of the heated perimeter of a steel section exposed to fire to the cross-sectional area of the same steel.

All column and beam sections have their own specific Hp/A ratio. Please consult Promat to establish the Hp/A ratio for a particular beam or column section and to ascertain the required thickness of Cafco SPRAYFILM® WB3.

For advice on thickness calculations for I and H section beams and columns, castellated sections, composite floors, upgrading of concrete slabs and more complex situations, please contact Promat.

See the tables on pages 4 to 10 on thickness for the fire resistance required.

HEALTH AND SAFETY

Adequate ventilation must be provided during use. Avoid contact with the skin and eyes by using eye protection, gloves, barrier cream and a face mask.

If the product comes into contact with the skin, wash immediately with soap and water. If the eyes are affected, flush with plenty of water and seek medical attention immediately.

A safety data sheet is available from Promat upon request.

Promat activities are conducted with due regard to all statutory requirements with appropriate safeguards against exposing employees and the public to health and safety risks.



Cafco SPRAYFILM® WB3

Water Based Intumescent Coating

FIRE PROTECTION THICKNESS

TABLE 1 Cafco SPRAYFILM® WB3 thicknesses for H section columns (4-sided exposure). Critical temperature 550°C. (AS1530: Part 4)

Hp/A	Thickness for the fire resistance required			
	30 min	60 min	90 min	120 min
Up to 45	0.23mm	0.60mm	1.50mm	1.50mm
46-50	0.23mm	0.60mm	1.50mm	1.50mm
51-55	0.23mm	0.60mm	1.50mm	1.50mm
56-60	0.23mm	0.60mm	1.50mm	1.50mm
61-65	0.23mm	0.60mm	1.50mm	1.50mm
66-70	0.23mm	0.60mm	1.50mm	1.67mm
71-75	0.23mm	0.60mm	1.50mm	1.83mm
76-80	0.23mm	0.60mm	1.50mm	2.00mm
81-85	0.23mm	0.60mm	1.50mm	2.08mm
86-90	0.23mm	0.60mm	1.50mm	2.15mm
91-95	0.23mm	0.60mm	1.50mm	2.23mm
96-100	0.23mm	0.60mm	1.50mm	2.31mm
101-105	0.23mm	0.60mm	1.50mm	2.38mm
106-110	0.23mm	0.60mm	1.50mm	2.46mm
111-115	0.23mm	0.60mm	1.50mm	2.54mm
116-120	0.23mm	0.60mm	1.50mm	2.62mm
121-125	0.23mm	0.66mm	1.57mm	2.69mm
126-130	0.23mm	0.71mm	1.62mm	2.77mm
131-135	0.23mm	0.75mm	1.67mm	2.85mm
136-140	0.23mm	0.80mm	1.72mm	2.92mm
141-145	0.23mm	0.85mm	1.78mm	3.00mm
146-150	0.23mm	0.87mm	1.83mm	3.11mm
151-155	0.23mm	0.88mm	1.88mm	3.23mm
156-160	0.24mm	0.89mm	1.93mm	3.34mm
161-165	0.24mm	0.90mm	1.98mm	3.45mm
166-170	0.24mm	0.90mm	2.03mm	3.57mm
171-175	0.24mm	0.91mm	2.08mm	3.68mm
176-180	0.24mm	0.92mm	2.14mm	3.80mm

Hp/A	Thickness for the fire resistance required			
	30 min	60 min	90 min	120 min
181-185	0.25mm	0.92mm	2.19mm	3.91mm
186-190	0.25mm	0.93mm	2.24mm	4.02mm
191-195	0.25mm	0.94mm	2.29mm	4.43mm
196-200	0.25mm	0.95mm	2.34mm	4.79mm
201-205	0.25mm	0.95mm	2.40mm	5.14mm
206-210	0.26mm	0.96mm	2.45mm	5.50mm
211-215	0.26mm	0.97mm	2.50mm	5.86mm
216-220	0.27mm	0.97mm	2.55mm	6.21mm
221-225	0.27mm	0.98mm	2.60mm	–
226-230	0.28mm	0.99mm	2.66mm	–
231-235	0.28mm	1.00mm	2.71mm	–
236-240	0.29mm	1.00mm	2.76mm	–
241-245	0.29mm	1.04mm	2.81mm	–
246-250	0.30mm	1.06mm	2.86mm	–
251-255	0.30mm	1.09mm	2.92mm	–
256-260	0.31mm	1.12mm	2.97mm	–
261-265	0.31mm	1.14mm	3.02mm	–
266-270	0.32mm	1.17mm	3.14mm	–
271-275	0.32mm	1.19mm	3.24mm	–
276-280	0.33mm	1.22mm	3.34mm	–
281-285	0.33mm	1.25mm	3.44mm	–
286-290	0.34mm	1.27mm	3.54mm	–
291-295	0.34mm	1.30mm	3.64mm	–
296-300	0.35mm	1.33mm	3.74mm	–
301-305	0.35mm	1.35mm	3.84mm	–
306-310	0.36mm	1.38mm	3.94mm	–
311-315	0.36mm	1.41mm	4.04mm	–
316-320	0.37mm	1.43mm	4.32mm	–



Cafco SPRAYFILM® WB3

Water Based Intumescent Coating

TABLE 2 Cafco SPRAYFILM® WB3 thicknesses for I section beams (3-sided exposure). Critical temperature 620°C, continuous concrete topping. (AS1530: Part 4)

Hp/A	Thickness for the fire resistance required				Hp/A	Thickness for the fire resistance required			
	30 min	60 min	90 min	120 min		30 min	60 min	90 min	120 min
Up to 45	0.23mm	0.25mm	1.20mm	1.20mm	181-185	0.23mm	0.67mm	1.83mm	2.95mm
46-50	0.23mm	0.25mm	1.20mm	1.20mm	186-190	0.23mm	0.70mm	1.95mm	3.01mm
51-55	0.23mm	0.25mm	1.20mm	1.20mm	191-195	0.23mm	0.73mm	2.02mm	3.18mm
56-60	0.23mm	0.25mm	1.20mm	1.20mm	196-200	0.23mm	0.76mm	2.07mm	3.33mm
61-65	0.23mm	0.25mm	1.20mm	1.20mm	201-205	0.23mm	0.80mm	2.11mm	3.48mm
66-70	0.23mm	0.25mm	1.20mm	1.23mm	206-210	0.23mm	0.83mm	2.15mm	3.64mm
71-75	0.23mm	0.25mm	1.20mm	1.28mm	211-215	0.24mm	0.86mm	2.19mm	3.79mm
76-80	0.23mm	0.27mm	1.20mm	1.33mm	216-220	0.24mm	0.88mm	2.23mm	3.94mm
81-85	0.23mm	0.28mm	1.20mm	1.39mm	221-225	0.24mm	0.89mm	2.27mm	4.21mm
86-90	0.23mm	0.30mm	1.20mm	1.44mm	226-230	0.24mm	0.91mm	2.31mm	4.57mm
91-95	0.23mm	0.32mm	1.20mm	1.49mm	231-235	0.24mm	0.93mm	2.36mm	4.93mm
96-100	0.23mm	0.34mm	1.20mm	1.63mm	236-240	0.25mm	0.94mm	2.40mm	5.29mm
101-105	0.23mm	0.36mm	1.20mm	1.78mm	241-245	0.25mm	0.96mm	2.44mm	5.64mm
106-110	0.23mm	0.38mm	1.20mm	1.94mm	246-250	0.25mm	0.97mm	2.48mm	6.00mm
111-115	0.23mm	0.40mm	1.20mm	2.04mm	251-255	0.25mm	0.99mm	2.52mm	-
116-120	0.23mm	0.42mm	1.20mm	2.10mm	256-260	0.25mm	1.00mm	2.56mm	-
121-125	0.23mm	0.44mm	1.20mm	2.17mm	261-265	0.26mm	1.02mm	2.60mm	-
126-130	0.23mm	0.46mm	1.20mm	2.23mm	266-270	0.26mm	1.04mm	2.64mm	-
131-135	0.23mm	0.48mm	1.20mm	2.30mm	271-275	0.27mm	1.05mm	2.69mm	-
136-140	0.23mm	0.50mm	1.20mm	2.36mm	276-280	0.28mm	1.07mm	2.73mm	-
141-145	0.23mm	0.52mm	1.20mm	2.43mm	281-285	0.28mm	1.08mm	2.77mm	-
146-150	0.23mm	0.54mm	1.26mm	2.49mm	286-290	0.29mm	1.10mm	2.81mm	-
151-155	0.23mm	0.56mm	1.31mm	2.56mm	291-295	0.29mm	1.11mm	2.85mm	-
156-160	0.23mm	0.57mm	1.37mm	2.62mm	296-300	0.30mm	1.13mm	2.89mm	-
161-165	0.23mm	0.57mm	1.42mm	2.69mm	301-305	0.30mm	1.14mm	2.93mm	-
166-170	0.23mm	0.57mm	1.48mm	2.75mm	306-310	0.31mm	1.16mm	2.98mm	-
171-175	0.23mm	0.61mm	1.58mm	2.82mm	311-315	0.31mm	1.18mm	3.02mm	-
176-180	0.23mm	0.64mm	1.70mm	2.88mm	316-320	0.32mm	1.19mm	3.22mm	-

Cafco SPRAYFILM® WB3

Water Based Intumescent Coating

FIRE PROTECTION THICKNESS

TABLE 3 Cafco SPRAYFILM® WB3 thicknesses for hollow section beams and columns (4-sided exposure). Critical temperature 550°C. (AS1530: Part 4)

Hp/A	Thickness for the fire resistance required				Hp/A	Thickness for the fire resistance required			
	30 min	60 min	90 min	120 min		30 min	60 min	90 min	120 min
Up to 45	0.23mm	0.40mm	1.80mm	3.50mm	181-185	0.41mm	1.27mm	3.43mm	–
46-50	0.23mm	0.40mm	1.80mm	3.50mm	186-190	0.41mm	1.30mm	3.48mm	–
51-55	0.23mm	0.42mm	1.80mm	3.50mm	191-195	0.42mm	1.32mm	3.57mm	–
56-60	0.23mm	0.44mm	1.80mm	3.50mm	196-200	0.42mm	1.35mm	3.70mm	–
61-65	0.23mm	0.47mm	1.80mm	3.50mm	201-205	0.43mm	1.37mm	3.82mm	–
66-70	0.23mm	0.49mm	1.80mm	3.50mm	206-210	0.43mm	1.40mm	3.94mm	–
71-75	0.24mm	0.51mm	1.92mm	3.50mm	211-215	0.44mm	1.42mm	4.06mm	–
76-80	0.24mm	0.53mm	2.07mm	3.50mm	216-220	0.44mm	1.44mm	4.19mm	–
81-85	0.25mm	0.56mm	2.20mm	3.50mm	221-225	0.45mm	1.47mm	4.31mm	–
86-90	0.25mm	0.58mm	2.34mm	3.50mm	226-230	0.45mm	1.49mm	4.43mm	–
91-95	0.25mm	0.60mm	2.47mm	3.50mm	231-235	0.46mm	1.52mm	4.55mm	–
96-100	0.26mm	0.66mm	2.54mm	3.50mm	236-240	0.46mm	1.54mm	4.68mm	–
101-105	0.27mm	0.72mm	2.59mm	3.67mm	241-245	0.47mm	1.56mm	4.80mm	–
106-110	0.28mm	0.78mm	2.65mm	3.94mm	246-250	0.47mm	1.59mm	4.92mm	–
111-115	0.28mm	0.84mm	2.70mm	4.22mm	251-255	0.48mm	1.61mm	5.04mm	–
116-120	0.29mm	0.90mm	2.75mm	4.50mm	256-260	0.48mm	1.64mm	5.17mm	–
121-125	0.30mm	0.96mm	2.80mm	4.78mm	261-265	0.49mm	1.66mm	5.29mm	–
126-130	0.31mm	1.02mm	2.85mm	5.06mm	266-270	0.49mm	1.68mm	5.41mm	–
131-135	0.32mm	1.03mm	2.91mm	5.33mm	271-275	0.50mm	1.71mm	5.53mm	–
136-140	0.33mm	1.06mm	2.96mm	5.61mm	276-280	0.50mm	1.73mm	5.56mm	–
141-145	0.34mm	1.08mm	3.01mm	5.89mm	281-285	0.50mm	1.76mm	5.78mm	–
146-150	0.35mm	1.11mm	3.06mm	6.17mm	286-290	0.51mm	1.78mm	5.90mm	–
151-155	0.36mm	1.13mm	3.11mm	6.44mm	291-295	0.51mm	1.80mm	6.02mm	–
156-160	0.37mm	1.15mm	3.17mm	–	296-300	0.52mm	1.86mm	6.15mm	–
161-165	0.38mm	1.18mm	3.22mm	–	301-305	0.52mm	1.90mm	6.27mm	–
166-170	0.39mm	1.20mm	3.27mm	–	306-310	0.53mm	1.95mm	6.39mm	–
171-175	0.40mm	1.23mm	3.32mm	–	311-315	0.53mm	1.99mm	6.51mm	–
176-180	0.40mm	1.25mm	3.38mm	–	316-320	0.54mm	2.04mm	–	–



Cafco SPRAYFILM® WB3

Water Based Intumescent Coating

TABLE 4 Cafco SPRAYFILM® WB3 thicknesses for I section beams (3-sided exposure). Critical temperature 620°C, continuous concrete topping. (BS476: Part 21: 1987)

Hp/A	Thickness for the fire resistance required			
	30 min	60 min	90 min	120 min
Up to 45	0.23mm	0.25mm	1.20mm	1.20mm
46-50	0.23mm	0.25mm	1.20mm	1.20mm
51-55	0.23mm	0.25mm	1.20mm	1.20mm
56-60	0.23mm	0.25mm	1.20mm	1.20mm
61-65	0.23mm	0.25mm	1.20mm	1.20mm
66-70	0.23mm	0.25mm	1.20mm	1.20mm
71-75	0.23mm	0.25mm	1.20mm	1.20mm
76-80	0.23mm	0.27mm	1.20mm	1.23mm
81-85	0.23mm	0.28mm	1.20mm	1.32mm
86-90	0.23mm	0.30mm	1.20mm	1.40mm
91-95	0.23mm	0.32mm	1.20mm	1.48mm
96-100	0.23mm	0.34mm	1.20mm	1.70mm
101-105	0.23mm	0.36mm	1.20mm	1.95mm
106-110	0.23mm	0.38mm	1.20mm	2.05mm
111-115	0.23mm	0.40mm	1.20mm	2.11mm
116-120	0.23mm	0.42mm	1.20mm	2.17mm
121-125	0.23mm	0.44mm	1.20mm	2.23mm
126-130	0.23mm	0.46mm	1.20mm	2.29mm
131-135	0.23mm	0.48mm	1.20mm	2.35mm
136-140	0.23mm	0.50mm	1.20mm	2.41mm
141-145	0.23mm	0.52mm	1.20mm	2.47mm
146-150	0.23mm	0.54mm	1.26mm	2.53mm
151-155	0.23mm	0.56mm	1.31mm	2.59mm
156-160	0.23mm	0.57mm	1.37mm	2.65mm
161-165	0.23mm	0.57mm	1.42mm	2.71mm
166-170	0.23mm	0.57mm	1.48mm	2.77mm
171-175	0.23mm	0.61mm	1.58mm	2.83mm
176-180	0.23mm	0.64mm	1.70mm	2.89mm

Hp/A	Thickness for the fire resistance required			
	30 min	60 min	90 min	120 min
181-185	0.23mm	0.67mm	1.83mm	2.95mm
186-190	0.23mm	0.70mm	1.95mm	3.01mm
191-195	0.23mm	0.73mm	2.02mm	3.40mm
196-200	0.23mm	0.76mm	2.07mm	3.73mm
201-205	0.23mm	0.80mm	2.11mm	4.07mm
206-210	0.23mm	0.83mm	2.15mm	4.26mm
211-215	0.24mm	0.86mm	2.19mm	4.48mm
216-220	0.24mm	0.88mm	2.23mm	4.70mm
221-225	0.24mm	0.89mm	2.27mm	4.91mm
226-230	0.24mm	0.91mm	2.31mm	5.13mm
231-235	0.24mm	0.93mm	2.36mm	5.35mm
236-240	0.25mm	0.94mm	2.40mm	5.57mm
241-245	0.25mm	0.96mm	2.44mm	5.78mm
246-250	0.25mm	0.97mm	2.48mm	6.00mm
251-255	0.25mm	0.99mm	2.52mm	6.22mm
256-260	0.25mm	1.00mm	2.56mm	6.43mm
261-265	0.26mm	1.02mm	2.60mm	–
266-270	0.26mm	1.04mm	2.64mm	–
271-275	0.27mm	1.05mm	2.69mm	–
276-280	0.28mm	1.07mm	2.73mm	–
281-285	0.28mm	1.08mm	2.77mm	–
286-290	0.29mm	1.10mm	2.81mm	–
291-295	0.29mm	1.11mm	2.85mm	–
296-300	0.30mm	1.13mm	2.89mm	–
301-305	0.30mm	1.14mm	2.93mm	–
306-310	0.31mm	1.16mm	2.98mm	–
311-315	0.31mm	1.18mm	3.02mm	–
316-320	0.32mm	1.19mm	3.22mm	–

NOTE: The above tables are based on report no. WF 176738A.

Cafco SPRAYFILM® WB3

Water Based Intumescent Coating

FIRE PROTECTION THICKNESS

TABLE 5 Cafco SPRAYFILM® WB3 thicknesses for I section beams (4-sided exposure). Critical temperature 550°C. (BS476: Part 21: 1987)

Hp/A	Thickness for the fire resistance required				Hp/A	Thickness for the fire resistance required			
	30 min	60 min	90 min	120 min		30 min	60 min	90 min	120 min
Up to 45	0.23mm	0.57mm	1.20mm	1.20mm	181-185	0.24mm	0.98mm	2.38mm	4.58mm
46-50	0.23mm	0.57mm	1.20mm	1.20mm	186-190	0.24mm	1.00mm	2.43mm	4.80mm
51-55	0.23mm	0.57mm	1.20mm	1.22mm	191-195	0.24mm	1.01mm	2.48mm	5.02mm
56-60	0.23mm	0.57mm	1.20mm	1.33mm	196-200	0.25mm	1.03mm	2.54mm	5.24mm
61-65	0.23mm	0.57mm	1.20mm	1.44mm	201-205	0.25mm	1.05mm	2.59mm	5.47mm
66-70	0.23mm	0.57mm	1.20mm	1.53mm	206-210	0.25mm	1.07mm	2.64mm	5.69mm
71-75	0.23mm	0.57mm	1.20mm	1.82mm	211-215	0.25mm	1.08mm	2.69mm	5.91mm
76-80	0.23mm	0.57mm	1.20mm	2.05mm	216-220	0.26mm	1.10mm	2.75mm	6.13mm
81-85	0.23mm	0.57mm	1.20mm	2.09mm	221-225	0.27mm	1.12mm	2.80mm	6.36mm
86-90	0.23mm	0.57mm	1.20mm	2.17mm	226-230	0.27mm	1.13mm	2.85mm	6.58mm
91-95	0.23mm	0.57mm	1.20mm	2.25mm	231-235	0.28mm	1.15mm	2.91mm	–
96-100	0.23mm	0.57mm	1.20mm	2.33mm	236-240	0.29mm	1.17mm	2.96mm	–
101-105	0.23mm	0.57mm	1.21mm	2.41mm	241-245	0.30mm	1.18mm	3.01mm	–
106-110	0.23mm	0.57mm	1.27mm	2.48mm	246-250	0.30mm	1.20mm	3.18mm	–
111-115	0.23mm	0.57mm	1.33mm	2.56mm	251-255	0.31mm	1.22mm	3.32mm	–
116-120	0.23mm	0.57mm	1.38mm	2.64mm	256-260	0.32mm	1.25mm	3.47mm	–
121-125	0.23mm	0.57mm	1.44mm	2.72mm	261-265	0.32mm	1.27mm	3.62mm	–
126-130	0.23mm	0.63mm	1.50mm	2.80mm	266-270	0.33mm	1.30mm	3.76mm	–
131-135	0.23mm	0.68mm	1.63mm	2.88mm	271-275	0.34mm	1.32mm	3.91mm	–
136-140	0.23mm	0.74mm	1.76mm	2.95mm	276-280	0.35mm	1.34mm	4.06mm	–
141-145	0.23mm	0.79mm	1.89mm	3.03mm	281-285	0.35mm	1.37mm	4.18mm	–
146-150	0.23mm	0.85mm	2.03mm	3.24mm	286-290	0.36mm	1.39mm	4.30mm	–
151-155	0.23mm	0.88mm	2.06mm	3.41mm	291-295	0.37mm	1.41mm	4.43mm	–
156-160	0.23mm	0.90mm	2.12mm	3.59mm	296-300	0.38mm	1.44mm	4.56mm	–
161-165	0.23mm	0.91mm	2.17mm	3.76mm	301-305	0.38mm	1.46mm	4.68mm	–
166-170	0.23mm	0.93mm	2.22mm	3.93mm	306-310	0.39mm	1.49mm	4.81mm	–
171-175	0.24mm	0.95mm	2.27mm	4.13mm	311-315	0.40mm	1.51mm	4.94mm	–
176-180	0.24mm	0.96mm	2.33mm	4.36mm	316-320	0.40mm	1.54mm	5.06mm	–

NOTE: The above tables are based on report no. WF 176738A.



Cafco SPRAYFILM® WB3

Water Based Intumescent Coating

TABLE 6 Cafco SPRAYFILM® WB3 thicknesses for H section columns (4-sided exposure). Critical temperature 550°C.
(BS476: Part 21: 1987)

Hp/A	Thickness for the fire resistance required			
	30 min	60 min	90 min	120 min
Up to 45	0.23mm	0.60mm	1.00mm	1.50mm
46-50	0.23mm	0.60mm	1.00mm	1.50mm
51-55	0.23mm	0.60mm	1.00mm	1.50mm
56-60	0.23mm	0.60mm	1.00mm	1.50mm
61-65	0.23mm	0.60mm	1.00mm	1.50mm
66-70	0.23mm	0.60mm	1.00mm	1.75mm
71-75	0.23mm	0.60mm	1.00mm	2.00mm
76-80	0.23mm	0.60mm	1.00mm	2.07mm
81-85	0.23mm	0.60mm	1.00mm	2.14mm
86-90	0.23mm	0.60mm	1.01mm	2.21mm
91-95	0.23mm	0.60mm	1.10mm	2.29mm
96-100	0.23mm	0.60mm	1.19mm	2.36mm
101-105	0.23mm	0.60mm	1.28mm	2.43mm
106-110	0.23mm	0.60mm	1.36mm	2.50mm
111-115	0.23mm	0.60mm	1.45mm	2.57mm
116-120	0.23mm	0.60mm	1.53mm	2.64mm
121-125	0.23mm	0.66mm	1.61mm	2.71mm
126-130	0.23mm	0.71mm	1.69mm	2.79mm
131-135	0.23mm	0.75mm	1.77mm	2.86mm
136-140	0.23mm	0.80mm	1.85mm	2.93mm
141-145	0.23mm	0.85mm	1.94mm	3.00mm
146-150	0.23mm	0.87mm	2.02mm	3.19mm
151-155	0.23mm	0.88mm	2.05mm	3.37mm
156-160	0.24mm	0.89mm	2.10mm	3.56mm
161-165	0.24mm	0.90mm	2.14mm	3.74mm
166-170	0.24mm	0.90mm	2.18mm	3.93mm
171-175	0.24mm	0.91mm	2.23mm	4.13mm
176-180	0.24mm	0.92mm	2.27mm	4.36mm

Hp/A	Thickness for the fire resistance required			
	30 min	60 min	90 min	120 min
181-185	0.25mm	0.92mm	2.32mm	4.58mm
186-190	0.25mm	0.93mm	2.36mm	4.80mm
191-195	0.25mm	0.94mm	2.40mm	5.02mm
196-200	0.25mm	0.95mm	2.45mm	5.24mm
201-205	0.25mm	0.95mm	2.49mm	5.47mm
206-210	0.26mm	0.96mm	2.54mm	5.69mm
211-215	0.26mm	0.97mm	2.58mm	5.91mm
216-220	0.27mm	0.97mm	2.62mm	6.13mm
221-225	0.27mm	0.98mm	2.67mm	6.36mm
226-230	0.28mm	0.99mm	2.71mm	6.58mm
231-235	0.28mm	1.00mm	2.75mm	–
236-240	0.29mm	1.00mm	2.80mm	–
241-245	0.29mm	1.04mm	2.84mm	–
246-250	0.30mm	1.06mm	2.89mm	–
251-255	0.30mm	1.09mm	2.93mm	–
256-260	0.31mm	1.12mm	2.97mm	–
261-265	0.31mm	1.14mm	3.02mm	–
266-270	0.32mm	1.17mm	3.14mm	–
271-275	0.32mm	1.19mm	3.24mm	–
276-280	0.33mm	1.22mm	3.34mm	–
281-285	0.33mm	1.25mm	3.44mm	–
286-290	0.34mm	1.27mm	3.54mm	–
291-295	0.34mm	1.30mm	3.64mm	–
296-300	0.35mm	1.33mm	3.74mm	–
301-305	0.35mm	1.35mm	3.84mm	–
306-310	0.36mm	1.38mm	3.94mm	–
311-315	0.36mm	1.41mm	4.04mm	–
316-320	0.37mm	1.43mm	4.32mm	–

NOTE: The above tables are based on report no. WF 176738A.

Cafco SPRAYFILM® WB3

Water Based Intumescent Coating

FIRE PROTECTION THICKNESS

TABLE 7 Cafco SPRAYFILM® WB3 thicknesses for hollow section beams and columns (4-sided exposure). Critical temperature 550°C. (BS476: Part 21: 1987)

Hp/A	Thickness for the fire resistance required				Hp/A	Thickness for the fire resistance required			
	30 min	60 min	90 min	120 min		30 min	60 min	90 min	120 min
Up to 45	0.23mm	0.40mm	1.80mm	3.50mm	181-185	0.41mm	1.27mm	3.43mm	–
46-50	0.23mm	0.40mm	1.80mm	3.50mm	186-190	0.41mm	1.30mm	3.48mm	–
51-55	0.23mm	0.42mm	1.80mm	3.50mm	191-195	0.42mm	1.32mm	3.57mm	–
56-60	0.23mm	0.44mm	1.80mm	3.50mm	196-200	0.42mm	1.35mm	3.70mm	–
61-65	0.23mm	0.47mm	1.80mm	3.50mm	201-205	0.43mm	1.37mm	3.82mm	–
66-70	0.23mm	0.49mm	1.80mm	3.50mm	206-210	0.43mm	1.40mm	3.94mm	–
71-75	0.24mm	0.51mm	1.93mm	3.50mm	211-215	0.44mm	1.42mm	4.06mm	–
76-80	0.24mm	0.53mm	2.07mm	3.50mm	216-220	0.44mm	1.44mm	4.19mm	–
81-85	0.25mm	0.56mm	2.20mm	3.50mm	221-225	0.45mm	1.47mm	4.31mm	–
86-90	0.25mm	0.58mm	2.34mm	3.50mm	226-230	0.45mm	1.49mm	4.43mm	–
91-95	0.25mm	0.60mm	2.47mm	3.50mm	231-235	0.46mm	1.52mm	4.55mm	–
96-100	0.26mm	0.66mm	2.54mm	3.50mm	236-240	0.46mm	1.54mm	4.68mm	–
101-105	0.27mm	0.72mm	2.59mm	3.67mm	241-245	0.47mm	1.56mm	4.80mm	–
106-110	0.28mm	0.78mm	2.65mm	3.94mm	246-250	0.47mm	1.59mm	4.92mm	–
111-115	0.28mm	0.84mm	2.70mm	4.22mm	251-255	0.48mm	1.61mm	5.04mm	–
116-120	0.29mm	0.90mm	2.75mm	4.50mm	256-260	0.48mm	1.64mm	5.17mm	–
121-125	0.30mm	0.96mm	2.80mm	4.78mm	261-265	0.49mm	1.66mm	5.29mm	–
126-130	0.31mm	1.02mm	2.85mm	5.06mm	266-270	0.49mm	1.68mm	5.41mm	–
131-135	0.32mm	1.03mm	2.91mm	5.33mm	271-275	0.50mm	1.71mm	5.53mm	–
136-140	0.33mm	1.06mm	2.96mm	5.61mm	276-280	0.50mm	1.73mm	5.66mm	–
141-145	0.34mm	1.08mm	3.01mm	5.89mm	281-285	0.50mm	1.76mm	5.78mm	–
146-150	0.35mm	1.11mm	3.06mm	6.17mm	286-290	0.51mm	1.78mm	5.90mm	–
151-155	0.36mm	1.13mm	3.11mm	6.44mm	291-295	0.51mm	1.80mm	6.02mm	–
156-160	0.37mm	1.15mm	3.17mm	–	296-300	0.52mm	1.86mm	6.15mm	–
161-165	0.38mm	1.18mm	3.22mm	–	301-305	0.52mm	1.90mm	6.27mm	–
166-170	0.39mm	1.20mm	3.27mm	–	306-310	0.53mm	1.95mm	6.39mm	–
171-175	0.40mm	1.23mm	3.32mm	–	311-315	0.53mm	1.99mm	6.51mm	–
176-180	0.40mm	1.25mm	3.38mm	–	316-320	0.54mm	2.04mm	–	–

NOTE: The above tables are based on report no. WF 176738B.



Cafco SPRAYFILM® WB3

Water Based Intumescent Coating

TOP COATING

In exposed and semi-exposed exterior environments, Cafco SPRAYFILM® WB3 should be coated with a compatible water resistant finish coat in order to give the desired colour and to seal the Cafco SPRAYFILM® WB3.

The topcoat system must be suitable for the environment in which it is to be used, and should be a good quality, long oil alkyd, silicone, acrylic latex or polyurethane type. All topcoats should be applied in accordance with the topcoat manufacturer's recommendations.

Ensure that the correct DFT of Cafco SPRAYFILM® WB3 is applied and is thoroughly dry before application of any top coat.

Typically, allow a minimum of 7 days for the Cafco SPRAYFILM® WB3 to fully cure before application of any top coat system.

For the top coat compatibility and minimum thickness requirements, always consult Promat.

PACKAGING

25kg plastic pails.

STORAGE

- Indoors in dry conditions between 10°C and 38°C.
- Protect from frost, excessive heat (above 45°C) and strong radiant sunlight.

SHELF LIFE

Maximum 10 months in original sealed containers.

ENVIRONMENTAL

Do not discharge into drains, watercourses or soil.



For latest information of the Promat Asia Pacific organisation, please refer to www.promat-ap.com

ASIA PACIFIC HEADQUARTERS

Promat International (Asia Pacific) Ltd.
Unit 19-02-01, Level 2 PNB Damansara
No.19 Lorong Dungun, Damansara Heights
50490 Kuala Lumpur
MALAYSIA
Tel: +60 (3) 2095 5111
Fax: +60 (3) 2095 6111
Email: info@promat-ap.com

AUSTRALIA

Promat Australia Pty. Ltd.
1 Scotland Road
Mile End South, SA 5031
Tel: 1800 PROMAT (776 628)
Fax: +61 (8) 8352 1014
Email: mail@promat.com.au

New South Wales Office **Promat Australia Pty. Ltd.**

Unit 1, 175 Briens Road
Northmead, NSW 2152
Tel: 1800 PROMAT (776 628)
Fax: +61 (2) 9630 0258
Email: mail@promat.com.au

Victoria Office

Promat Australia Pty. Ltd.
Suite 205, 198 Harbour Esplanade
Docklands, VIC 3008
Tel: 1800 PROMAT (776 628)
Fax: 1800 334 598
Email: mail@promat.com.au

Queensland Office

Promat Australia Pty. Ltd.
Unit 2 Level 1
49 Gregory Tce
Spring Hill, QLD 4000
Tel: 1800 011 376
Fax: 1800 334 598
Email: mail@promat.com.au

CHINA

Promat China Ltd.
Room 503, Block B, Qi Lin Plaza
13-35 Pan Fu Road
510180 Guangzhou
Tel: +86 (20) 8136 1167
Fax: +86 (20) 8136 1372
Email: info@promat.com.cn

Beijing Office

Promat North China
(Division of Promat China Ltd.)
Room 1507 Building 5, SOHO Xiandaicheng
No.88 Jianguo Road, Chaoyang District
100022 Beijing
Tel: +86 (10) 8589 1254
Fax: +86 (10) 8589 2904
Email: info@promat.com.cn

For Promat International groups worldwide:
www.promat-international.com

1. This document is produced on the basis of information and experience available at the time of preparation. Promat is constantly reviewing and updating all of its test data and reserves the right to change products and specifications without notice.
2. Promat is not responsible if recipients of fire test reports, assessments or literature incorrectly interpret said contents and use products based on those interpretations.

HONG KONG

Promat International (Asia Pacific) Ltd.
Room 1010, C.C. Wu Building
302-308 Hennessy Road
Wanchai
Tel: +852 2836 3692
Fax: +852 2834 4313
Email: spraysinfo@promat-ap.com

INDIA

Promat International (Asia Pacific) Ltd.
(India Representative Office)
610-611, Ansal Imperial Tower
C-Block, Community Centre
Naraina Vihar, Naraina
110028 New Delhi
Tel: +91 (11) 2577 8413
Fax: +91 (11) 2577 8414
Email: spraysinfo@promat-ap.com

Bangalore Office

Promat International (Asia Pacific) Ltd.
(India Representative Office)
Cabin No.BC-9 & BC-10
Oculus Workspaces, No.66/1, 2nd Floor
Coles Road, Frazer Town
560005 Bangalore
Tel: +91 (80) 4031 4151
Fax: +91 (80) 4125 2135
Email: spraysinfo@promat-ap.com

Mumbai Office

Promat International (Asia Pacific) Ltd.
(India Representative Office)
Stylus Serviced Offices
Ground Floor, Velocity
Phase 1, Logitech Park
Andheri Kurla Road, Andheri East
400072 Mumbai
Tel: +91 (22) 6769 4567
Fax: +91 (22) 6769 4568
Email: spraysinfo@promat-ap.com

MALAYSIA

Promat (Malaysia) Sdn. Bhd.
Unit 19-02-01, Level 2 PNB Damansara
No.19 Lorong Dungun, Damansara Heights
50490 Kuala Lumpur
Tel: +60 (3) 2095 8555
Fax: +60 (3) 2095 2111
Email: spraysinfo@promat-ap.com

SINGAPORE

Promat Building System Pte. Ltd.
10 Science Park Road, #03-14 The Alpha,
Singapore Science Park II
Singapore 117684
Tel: +65 6776 7635
Fax: +65 6776 7624
Email: spraysinfo@promat-ap.com

Your local Promat supplier

